

## TECHNICAL DATA SHEET

Revision date: 06.02.2025

## AEROSOL UV PRIMER

Article number:	26033						
Colour:	grey semi-transparent						
Intended use:	Car refinishing product/ Primer						
General characteristics:	<p>High-quality UV-drying primer for fast and economic refinishes. It can be sanded after only 3 min irradiation by a UV-A 400 W LED-Light, a mercury vapor lamp or 4-5 min exposure to direct sunlight. The UV curing process is faster and saves a lot on heating costs. At the same time, cycle times are reduced as the priming phase is not interrupted by heating intervals.</p> <ul style="list-style-type: none"><li>▪ substrates don't have to be heated</li><li>▪ UV curing eliminates the cooling phase prior to sanding</li><li>▪ outstanding mechanical and chemical resistance</li><li>▪ perfectly suitable for spot repairs</li><li>▪ excellent adhesion</li><li>▪ ready to use – no activation or mixing is needed</li><li>▪ easy to sand</li></ul> <p><b>Substrates:</b></p> <table><tr><td>▪ steel</td><td>▪ galvanized steel</td></tr><tr><td>▪ putties / fiber glass</td><td>▪ plastics (PU,ABS,PVC,PC,PS)</td></tr><tr><td>▪ aluminium</td><td>▪ old paint coatings</td></tr></table>	▪ steel	▪ galvanized steel	▪ putties / fiber glass	▪ plastics (PU,ABS,PVC,PC,PS)	▪ aluminium	▪ old paint coatings
▪ steel	▪ galvanized steel						
▪ putties / fiber glass	▪ plastics (PU,ABS,PVC,PC,PS)						
▪ aluminium	▪ old paint coatings						

## TECHNICAL CHARACTERISTICS

**Base:** resin**Smell:** characteristic**Consumption:** 2.5 - 3 m<sup>2</sup> (400 ml)**DFT:** 40 - 50 µ (1 - 2 layers)

## ■ Substrate pre-treatment:

The substrate must be clean, dry, free from rust and grease. Remove old loose coatings and primers

Old paint coating	Degrease, dry sand with P220-320, blow off, degrease again
Galvanized steel	Degrease, dry sand with P220-320, blow off, degrease again
Aluminium	Degrease, dry sand P220-320 or mat with an abrasive finishing pad, degrease again
Steel	Degrease, dry sand with P120-320, blow off, degrease again
Plastics	Degrease, mat with an abrasive finishing pad, degrease again

## APPLICATION PROCESS

Before use, carefully read and observe the warning texts on the label!

### Processing conditions:

Please only use in an adequately ventilated environment with an ample supply of fresh air. Processing temperature should be at least +12 °C and max. air humidity should not exceed 80%.

### Processing tips:

- Beforehand, mask the parts that shouldn't be painted
- Degrease the surface
- Wear a respirator (type A2/P3 is recommended)
- The aerosol should have room temperature
- Before use, shake the aerosol for 2 min and spray a sample
- Apply the UV Primer in 1 - 2 layers at a dry film thickness of 40 - 50 µm
- Distance to the surface should be approximately 10 - 15 cm
- Flash off time: cure with 400W UV-A lamp for 5 min between each layer
- Dry to handle after 5 min if the sprayed area is constantly being irradiated by the UV-A lamp
- Drying time depends on intensity, power, light spectral (365 - 395nm), bulb service life and performance of the lamp, distance of the lamp to the surface and film thickness.
- Clean the valve after use (turn aerosol upside down and press the nozzle for approximately 5 sec)

### ATTENTION:

- We recommend carrying out a test on a sample sheet before actual use.
- After drying, slightly sticky residues may remain on the surface of the filler. These should be removed with silicone remover or old sanding paper before final sanding.

### Sanding:

Sand step by step with sandpapers P320, P400, P500 and finally with P800 if colour shade requires.

### VOC regulation:

EU limit value: Category B/e 840 g/l

This product contains max. 657.2 g/l VOC



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH  
RUDOLF-DIESEL-STRASSE 8A  
69115 HEIDELBERG  
GERMANY

FON 0049 (0) 6221 - 520 440  
FAX 0049 (0) 6221 - 520 449  
MAIL [INFO@CHAMAELEON-PRODUKTION.DE](mailto:INFO@CHAMAELEON-PRODUKTION.DE)  
WEB [WWW.CHAMAELEON-PRODUKTION.DE](http://WWW.CHAMAELEON-PRODUKTION.DE)

- **Shelf life:**  
24 months, if stored in tightly closed original container

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier under:

e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding Safety Data Sheet.

VAT NO. / UST-ID NR.: DE231468544  
EORI NO. / EORI NR.: DE6029442  
CEO / GESCHÄFTSFÜHRER: SASCHA HAGEMANN  
TRADE REGISTER NO. / HANDELSREGISTER NR.: AMTSGERICHT MANNHEIM HRB 9778  
Chamäleon GmbH – Technical Data Sheet

BANK: HEIDELBERGER VOLKSBANK EG  
IBAN: DE78 6729 0000 0042 8627 03  
BIC: GENODE61HD